



TECHNICAL SHEET

IDROSIL A

CONSOLIDATING MINERAL WATER

TO CEMENT SURFACES CHALKING

DESCRIPTION

IDROSIL A is an aqueous solution of silicic salts, indicated for the consolidation base surfaces and cementitious substrates with poor consistency or chalking. It is distinguished by the following characteristics: high penetration, total absence of VOC, no residual odor. This product is also suited for bonding ceramic and parquet on supports radians. It is flanked to the exclusive use of glues and epoxy primers and / or cement.

TECHNICAL DATA

Appearance: colorless transparent liquid.
 Type: aqueous solution of inorganic silicic salts
 Minimum application temperature: +12° C
 Specific weight: 1.38 Kg / L
 Pot Life: > 2h min. at 25° C
 Foot traffic after the application: 6/8 at 25° C
 Waiting time before installation: 5/7 days at 25° C

INDICATIONS

1. Do not use IDROSIL A together with solvents or products containing organic solvents.
2. Do not use the product on anhydrite, gypsum, marble, ceramic, etc.. (different from the cement composition).
3. Always check the humidity and the conditions of the substrate to be treated through the use of appropriate tools.
4. Before the application, acclimatize the product at a temperature between +15 ° C and 35 ° C.
5. Make sure that the laying environment has a value of relative humidity <70%.
6. Do not apply to wet surfaces.
7. Carefully remove dust formation saline after the drying of the support.
8. Caustic (clean immediately with water any drips of metal, marble, glass, ceramic).
9. For cleaning tools use water only.
10. When handling the product, use rubber gloves and goggles.

For any questions covering any changes in operations, contact your technical service.

SURFACE PREPARATION

The surfaces to be treated must be free of dust, mold release agents or other foreign materials.

PRODUCT PREPARATION

The product is ready for use.

APPLICATION

Apply directly to the substrate evenly distributing the product to avoid stagnation of material.

AVERAGE COVERAG WITH ROLLER BAG MEDIUM

400-600 gr / sqm. (depending on the installation surface).



TECHNICAL SHEET

STORAGE

The product keeps the warranty in its original packaging (not altered) under standard conditions (15-35 ° C and 35-70% RH) for a period of 12 months. It is important to keep the product in a dry and ventilated area away from heat and direct sunlight.

PACKAGING

PE tank 10 kg

NOTE

The information contained in this data sheet is based on our best knowledge and preparation. However, this cannot be interpreted as a commitment to guarantee, since the means, place of employment and the application conditions are beyond our control. So we do not assume any liability for unauthorized use of the product as the advice given in this application is indicative. In the case where there is any doubt about the application, it is recommended to perform preliminary tests.

The company Viscol s.n.c. therefore reserves the right to change or update this sheet without notice.

Users of the product are advised to check that you have the latest update.

IDROSIL A
CONSOLIDATING MINERAL WATER
TO CEMENT SURFACES CHALKING

BEFORE USING THE PRODUCT ALWAYS CONSULT MATERIAL SAFETY DATA SHEETS.