



## TECHNICAL SHEET

# MV80

SINGLE COMPONENT WATER PAINT  
FOR WOODEN FLOORS

### DESCRIPTION

**MV80** is a single-component paint water-based modified polyurethane resins, specific for parquet coating. Available in gloss, semi-gloss and matte. Easy to apply, enhances the natural characteristics of wood essence, giving it a warm tone and excellent surface coverage. Can be used in addition to the parquet for other wooden substrates such as skirting boards, beads, windows and wooden structures in general.

### TECHNICAL DATA

Appearance:	beige opalescent liquid.
Type:	acrylic-polyurethane paint in water dispersion
Gloss:	85 glossy gloss, semi-gloss 30 Gloss, matte 15 gloss.
Viscosity (Ford 4):	16 sec.
Specific weight:	1.03 Kg / lt
Pot Life:	> 2 h at 25° C
Dust:	25 min.
Surface drying:	3/5 hours
Sanding:	6/8 hours
Method and application:	brush, roller or spray.
Recoat:	after 6 - 8 hours
Application conditions:	between + 15° C and + 25° C with u.r. equal to 55% - 60%

The values shown here are calculated at standard conditions (25° C and 55% humidity).

### INDICATIONS

1. Do not apply the product in extremely cold and wet environment.
2. During application avoid air currents.
3. Acclimate the product before application.
4. Smooth the floor accurately using abrasive paper or retinas gradually: after filling grain 80/120; intermediate sanding between coats of paint grain 180/220. In this way, you can optimize the work and improve the final appearance.

**For any questions about changes to operations, contact your technical service.**

### SURFACE PREPARATION

The surface must be filled, smooth, perfectly clean and free of detaching or residues in general. For the application use clean containers and tools. It is advisable to apply as a first coat the bottom of the water waves to avoid color variations on some wood types. Apply the first coat of paint in a uniform and homogeneous, avoiding drafts. After drying, the floor can be sanded with fine sandpaper (180 - 220).

### PRODUCT PREPARATION

The product is ready to use: It is recommended to shake the container 1-2 minutes before application. The paint can also be used as a primer.



## TECHNICAL SHEET

# MV80

SINGLE COMPONENT WATER PAINT  
FOR WOODEN FLOORS

### APPLICATION

Apply the first coat of paint uniform and homogeneous, avoiding drafts. After drying, the floor can be sanded with fine sandpaper (180 - 220). Aspirate and repaint with two coats of the same product respecting the drying time between coats.

### AVERAGE COVERAGE WITH SHORT HAIR ROLLER

80-100 gr / sqm. (depending on the installation surface).

### STORAGE

The product keeps the warranty in its original packaging (not altered) under standard conditions (15-35 ° C and 35-70% RH) for a period of 12 months. It is important to keep the product in a dry and ventilated area away from heat and direct sunlight. Protect from frost.

### PACKAGING

PE tank of 5 liters or 10 liters

### NOTE

The information contained in this data sheet is based on our best knowledge and preparation.

However, this cannot be interpreted as a commitment to guarantee, since the means, place of employment and the application conditions are beyond our control. So we do not assume any liability for unauthorized use of the product as the advice given in this application is indicative. In the case where there is any doubt about the application, it is recommended to perform preliminary tests.

The company Viscol s.n.c. therefore reserves the right to change or update this sheet without notice.

Users of the product are advised to check that you have the latest update.

**BEFORE USING THE PRODUCT ALWAYS CONSULT MATERIAL SAFETY DATA SHEETS.**